

OUR PRODUCTS

OIL & GAS GRADES

AISI 4130 (~25CrMo4/SIS2225/25CD4) Rolled Bar Heat Treated and Tested

18-22 HRC (207 – 237 BHN) 75K Min Yield, NACE MR0175 & API 6A PSL 3

Size Range Ø 25mm to Ø 300 mm

AISI 4130 (~25CrMo4/SIS2225/25CD4) Forged Annealed Bar (Round)

Size Range Ø 250mm to Ø 1010 mm

AISI 4130 (~25CrMo4/SIS2225/25CD4) Forged Bar (Square)

Size Range 254mm Sqr to 510mm Sqr

AISI 8630HM Rolled Bar Heat Treated and Tested

18-22 HRC (207 – 237 BHN) 80K Min Yield, NACE MR0175 & API 6A PSL 3

Size Range Ø 50mm to Ø 290 mm

AISI 8630HM Forged Annealed Bar

Size Range Ø 250mm to Ø 775 mm

ASTM A182 F22 (~10CrMo9.10/SIS2218/10CD9.10/SIS2218/10CD9.10 Rolled Annealed Bar

Size Range Ø 76mm to Ø 279.4 mm

ASTM A182 F22 (~10CrMo9.10/SIS2218/10CD9.10/SIS2218/10CD9.10 Forged Annealed Bar

Size Range Ø 250mm to Ø 870 mm

AISI 4140 (~42CrMo4/SIS2244/42CD4) Rolled Bar Heat Treated and Tested

18-22 HRC (207 – 237 BHN) 80K Min Yield, NACE MR0175 & API 6A PSL 3

Size Range Ø 32mm to Ø 290

AISI 4140 (~42CrMo4/SIS2244/42CD4) Forged Annealed Bar

Size Range Ø 250mm to Ø 660 mm

OUR PRODUCTS

OIL & GAS GRADES cont.

AISI 4145HM Rolled Bar Heat Treated and Tested

30-36 HRC (285 - 341 BHN) Tested to API Spec 7

Size Range Ø 80mm to Ø 310 mm

AISI 4145HM Forged, Turned, Heat Treated and Tested to API Spec 7

Size Range Ø 310mm to Ø 510 mm

AISI 4340 Rolled Peeled Bar

(262 – 321 BHN) 105K Min Yield, Impacts at -32°C Heat Treated and Tested

Size Range Ø 50.8 mm to Ø 290 mm

AISI 4340 Black Annealed Bar

Size Range Ø 305 mm to Ø 485 mm

ASTM A350 LF2 Normalised and Tested

Tested to A350 LF2 / A105 including Impact Testing at -46°C

Size Range for Rolled Bar Ø 40 mm to Ø 300 mm, Size Range for Forged Bar Ø 300 mm to Ø 710 mm

ASTM A564 Gr.630 (17/4PH) Turned Bar (~ W Nr. 1.4542, X5CrNiCuNb 16 – 4)

Solution Treated, Double Aged & Tested to Double H1150 / NACE MR0175

Size Range Ø 9.25 mm to Ø 510 mm